

**Type Test Report**  
**Electrical Accessories and Hardware Reference Laboratory**


**Parallel Groove Connector Al 16-120 mm<sup>2</sup> / Al 16-120 mm<sup>2</sup>**  
**CO1005**

**Client: Council for Assessment and Compliance with Electrical Industry Equipment**  
**Production Standards, Power Generation, Transmission & Distribution Company**

**Manufacturer: Electro Niroo Taban Control Company (NETCO).**

**Test Standard: BS 3288-1 (2014), IEC 61238-1-3 (2018), EN 50483-6 (2009)**

**Niroo Research Institute**





**Parallel Groove Connector Al 16-120 mm<sup>2</sup> / Al 16-120 mm<sup>2</sup>  
CO1005**

Serial number: -

Reference Standards: BS 3288-1 (2014), IEC 61238-1-3 (2018), EN 50483-6 (2009)

This report has been reproduced by Electrical Accessories and Hardware Reference Laboratory, based on the original report No. CH140027, and at the request of the Electro Niroo Taban Control Company (NETCO).

Date of issue: 2025/05/10

**NRI**  
Niroo Research Institute

Reviewed by: H. Mostafavi



Approved by: F. Naghdi



---

**Parallel Groove Connector Al 16-120 mm<sup>2</sup> / Al 16-120 mm<sup>2</sup>  
CO1005**

Serial number: -

Reference Standards: BS 3288, IEC 61238, EN 50483-6

---

Tested by: M. Soltanloo

Approved by: A. Bajgholi

Tests witnessed by:

Date of issue: 2021/05/25

---

Laboratory: Electrical Accessories and Hardware Reference Laboratory

Address: Niroo Research Institute, End of Shahid Dadman Blvd., Shahrak Ghods, Tehran, Iran

Tel / Fax: (+98-21) 88079400 / (+98-21) 88078296

Website: www.nri.ac.ir

---

Client: Council for Assessment and Compliance with Electrical Industry Equipment Production  
Standards, Power Generation, Transmission & Distribution Company

Manufacturer: Electro Niroo Taban Control Company (NETCO)

Request number: 99/27500/1628

Request date: 2020/05/27

Sampling date: 2020/09/10

Sampling location: No. 10, Kamalzadeh St., End of Robat Mashin St., Shora Bly., Kamalshahr, Karaj


---

Report number: CH140027

Sample code: SCH140024

---

Remarks: Any reproduction of this report without the approval of the Electrical Accessories and  
Hardware Reference Laboratory is invalid.



---

Tested by: M. Soltanloo

Approved by: A. Bajgholi



## Contents

1. Summary of test results.....	5
2. Product Specifications .....	6
3. Technical Specifications .....	6
4. General Considerations.....	6
5. Test Methods and Results .....	7
5.1. Visual and dimensional examination .....	7
5.2. Mechanical tests.....	7
5.2.1. Slip test .....	7
5.2.2. Connector bolt tightening test.....	8
5.3. Corrosion test.....	10
5.4. Electrical ageing test.....	9
Appendix .....	11

**NRI**  
Niroo Research Institute



## 1. Summary of test results

Test	Test Type	Standard/Clause	Result
Visual and dimensional examination	Type test	BS 3288	Passed
Slip test	Type test	IEC 61238	Passed
Connector bolt tightening test	Type test	IEC 61238	Passed
Electrical ageing test	Type test	IEC 61238	Passed
Corrosion test	Type test	EN 50483-6	Passed

Parallel Groove Connector Al 16-120 mm<sup>2</sup> / Al 16-120 mm<sup>2</sup> CO1005 of Electro Niroo Taban Control Company (NETCO) is approved according to BS 3288, IEC 61238, and EN 50483-6 standards.


**NRI**  
Niroo Research Institute



## 2. Product Specifications

Name: Bimetallic Parallel Groove Connector Al 16-120 mm<sup>2</sup> / Al 16-120 mm<sup>2</sup>

Model: CO1005



## 3. Technical Specifications

Branch Conductor Range: Al 16-120 mm<sup>2</sup>

Main Conductor Range: Al 16-120 mm<sup>2</sup>

Features:

- 4 × Belleville washer with dacromat coating

- 2 × M8 bolt with dacromat coating and 2 × Al shear heads

Weight:

Installation Torque: 20 N.m

Markings:

## 4. General Considerations

The customer has the right to officially announce their written objection to the test results or procedure within one month after the test report is issued. The tested samples will be stored at the laboratory for up to 6 months after testing.

Sampling was conducted by representatives of the Niroo Research Institute.



## 5. Test Methods and Results

### 5.1. Visual and dimensional examination

The fitting was visually and dimensionally inspected in order to make sure that it is within standard tolerances.

#### Acceptance Criteria:

It shall be verified that the test samples are in accordance with the drawing provided by the manufacturer. Manufacturer's name shall be engraved on the sample.

#### Results:

The test samples were in accordance with the manufacturer's specifications. Manufacturer's name was engraved on the sample. The connector has 4 Belleville washers with 2.0 mm thickness with dacromat coating, 2 bolts of size M8 with 2 Al shear headss.

#### Conclusion:

The connector passed the test.

### 5.2. Mechanical tests

#### 5.2.1. Slip test

Al conductors with 120-120 mm<sup>2</sup> and 16-16 mm<sup>2</sup> were used in the test. The tensile force was  $40 \times A$ , where A was the conductor nominal cross section area in mm<sup>2</sup>.

#### Acceptance Criteria:

The conductor shall maintain the test load for 60 s without breaking or any damage that would prevent the correct function of the cable.

Sample	Conductor (mm <sup>2</sup> )	Standard load (N)	Slip load (N)
1	Al 120-120	4800	5900
2			6120
3	Al 16-16	640	1200
4			1245

#### Results:

The connector and the conductors withstood the applied loads and no slip, damage or failure were observed.

#### Conclusion:

The connector passed the test.



### 5.2.2. Shear head function test

To ensure that the shear head mechanism functions correctly within the specified torque range, four samples were tested at each of the minimum temperature of -10 °C and the maximum temperature of 50 °C using the following conductor cross section combinations.

Main Conductor (mm <sup>2</sup> )	Branch Conductor (mm <sup>2</sup> )	Shearing-off torque at the minimum temperature (N.m)	Shearing-off torque at the maximum temperature (N.m)
120 Al (Max.)	120 Al (Max.)	22.0 – 21.4 – 20.8 – 22.0	21.6 – 22.4 – 23.0 – 22.0
16 Al (Min.)	16 Al (Min.)	22.0 – 21.8 – 21.6 – 22.0	20.8 – 21.0 – 21.6 – 21.9

#### Acceptance Criteria:

For each of the test temperatures and cross section combination, the torque at which the shear head shears, shall be within the tolerances of the manufacturer's specified torque.

#### Results:

The shearing-off was taken place within the torque range of 20-22 N.m at -10 and within the torque range of 20-23 N.m at 50 °C, on the maximum and minimum conductor cross section combinations.

#### Conclusion:

The connector passed the test.

### 5.2.3. Connector bolt tightening test

The connector shall be installed on a conductor or cable with a diameter equal to that for which the connector is intended to be used. The bolts and/or nuts shall be tightened with the installation torque specified by the supplier (20 N.m). The torque shall be increased to the specified installation value by a factor of 1,1 (22 N.m). 10 installations and removals shall be completed. Finally, the torque shall be increased to either twice the specified installation value or the maximum torque value recommended by the bolt supplier; whichever is the lower.

#### Acceptance Criteria:

The threads must be usable for any number of subsequent tightening and loosening operations and all parts of the connector must remain intact. There must be no unacceptable damage to the conductor inside the connector.

#### Results:

The Al nuts were removed from the bolts at torques of 27.6, 29.4, 28.2 and 26.9 N.m.

#### Conclusion:

The connector passed the test.



### 5.3. Electrical ageing test

A test loop consisting of 6 connectors was prepared according to standard and subjected to 1000 heating and cooling cycles. The test was performed using a 120-120 mm<sup>2</sup> conductor. The resistance was measured 12 times during the test; first measurement was taken before heating/cooling cycles, the second one after first 250<sup>th</sup> cycle, and the remaining measurements after every 75 cycles thereafter.

#### Acceptance Criteria:

Maximum standard values for the test parameters are shown in the following table.

Parameter	Maximum value
Initial scatter, $\delta$	0.3
Mean scatter, $\beta$	0.3
Assessment of resistance stability	15 %
Resistance factor ratio, $\lambda$	2.0
Temperature stability $\Delta\theta_j$	$\Delta\theta_j - 10 \leq \Delta\theta_j \leq \Delta\theta_j + 10$
Maximum temperature $\theta_j$ of each connector	$\theta_R$

#### Results:

Results are shown in the following table.  
All samples fulfilled standard requirements.

#### Conclusion:

The connector passed the test.

Parameter	Maximum Standard Value	Connector 1		Connector 2		Connector 3		Connector 4		Connector 5		Connector 6	
Initial scatter, $\delta$	0.3	0.18											
Mean scatter, $\beta$	0.3	0.14											
Assessment of resistance stability	0.15	0.13		0.146		0.15 <sup>*</sup>		0.135		0.15 <sup>*</sup>		0.14	
Maximum temperature $\theta_j$ of each connector (°C)	140	102		98		120		128		121		119	
Resistance factor ratio, $\lambda$	1.5	1.3		1.5		1.4		1.5		1.3		1.3	
Primary torque (N.m)	-	20											
Secondary torque (N,m)	-	23.6	24.1	23.5	24.2	21.6	22.0	23.4	25.0	21.1	20.0	23.0	22.8
Torque drop (%)	-	41	40	41	39	46	45	41	37	47	50	42	43

\* Borderline



#### **5.4. Corrosion test**

According to EN 50483-6, clause 8.4., the samples exposed to 500 cycles of 2 h (1000 h) in an environment created by the solution consisting of 0.05 % sodium chloride (NaCl) and 0.35 % ammonium sulphate ((NH<sub>4</sub>)<sub>2</sub>SO<sub>4</sub>) by mass. After the test, the samples were subjected to visual inspection.

##### **Acceptance Criteria:**

Visual inspection shall be carried out and there shall be no significant trace of red rust. The amount of corroded area should not be more than 10 % of the exposed surface area of the metallic parts.

The connector's identification marking shall be legible when examined with normal or corrected vision, without magnification.

No deterioration of the connector occur which would impair their normal function.

##### **Results:**

No trace of red rust was observed.

The connector's identification marking was legible when examined with normal vision.

The sample fulfilled standard requirements.

##### **Conclusion:**

The connector passed the test.

**NRI**  
Niroo Research Institute



## Appendix

